



PRODUCT: GRO-LAC® QUICK DRY TO METAL FLAT WHITE

CODE: 766-1018

TYPE: COMPLEX ACRYLIC

PRODUCT DESCRIPTION: GRO-LAC® Quick Dry to Metal Flat White is a complex acrylic specially formulated to meet the requirements of replacing high VOC-containing solvent coatings. The performance of early air dry and low temperature bake coupled with easy application methods makes it an excellent replacement for solvent coatings. GRO-LAC® Quick Dry to Metal Flat White is also richly pigmented with Titanium Dioxide and an anti-corrosive pigment.

USES: Recommended for use on properly prepared interior or exterior steel and aluminum.

SURFACE PREPARATION: All surfaces to be coated should be free of dirt, wax, oil, grease, fingerprints, moisture, drawing compounds, or any other foreign substances that would cause loss of adhesion or coating failure. Pre-coat with a zinc or iron phosphate primer. Properly prepared surfaces assure good coating adhesion and good inner coat adhesion. Do not apply to cold metal substrates.

APPLICATION AND CLEAN UP: Stir thoroughly before use and occasionally during use. Stir gently as to not cause foaming. Check to make sure pigment is properly stirred in. For best results, apply a wet film thickness of 3.1 to 4.5 mils, creating a dry film thickness of 1.5 to 2.1 mils. This product may be applied with conventional equipment. For conventional spray: Reduce viscosity with water only to 25-30 seconds, No. 3 Zahn cup. For airless spray: Use as supplied in the container. Theoretical coverage: @1 mil-744 sq. ft., @2 mils-372 sq. ft., @3 mils-248 sq. ft., @4 mils-186 sq. ft. All equipment should be washed with clean, warm water after each use.

PRODUCT DATA

GROCO SPECIALTY COATINGS
10818 Hawn Freeway / Dallas, Texas 75217
972-286-7890 FAX 972-286-8890

www.grocosc.com



GRO-LAC® QUICK DRY TO METAL FLAT WHITE

SPECIFICATIONS: 766-1018

Solids by Weight	61.19 +/- 2.0%	
Solids by Volume	46.39 +/- 2.0%	
Theoretical Coverage (sq. ft./gal. @ 1 mil dry film)	744	
Viscosity (Krebs units @ 77 degrees F).....	66-72 K.U.	
Dry Time (@ 77 degrees F)	Touch	20-25 min.
	Re-Coat	1 hr.
Gloss (@ 60 degrees F)	5.4	

AVAILABILITY:

Colors: White

PRECAUTIONS: PROTECT FROM FREEZING! CAUTION! Close container after each use. Do not take internally. Keep out of the reach of children.

FOR FURTHER INFORMATION SEE MSDS SHEET.

PRODUCT DATA

GROCO SPECIALTY COATINGS
10818 Hawn Freeway / Dallas, Texas 75217
972-286-7890 FAX 972-286-8890

www.grocosc.com