



**PRODUCT:** GRO-LAC® QUICK DRY BRUSHING ENAMEL  
GLOSS WHITE

**CODE:** 766-1205

**TYPE:** ACRYLIC COPOLYMER EMULSION

**DESCRIPTION:** GRO-LAC® Quick Dry Brushing Enamel Gloss White was specially formulated to meet the requirements of early air dry, early water resistance and film hardness. GRO-LAC® Quick Dry Brushing Enamel Gloss White is richly pigmented and suspended in complex acrylic. It is a water-type vehicle system; therefore, it may be easily thinned with water to a desired dip or spray application.

**USES:** May be used for various types of general industrial metal and wood applications. It may be applied to properly treated wood, aluminum, cold roll steel, galvanized metal, copper and most metal substrates.

**SURFACE PREPARATION:** All substrates to be coated should be free of grease, oil, dirt, fingerprints, moisture, drawing compounds or any other foreign substances that would cause loss of adhesion or coating failure. Cold roll steel or iron: Treatment of the surface with a zinc or iron phosphate is recommended. For best results apply one coat of GRO-LAC® Anti-Corrosive Primer to the surface prior to top coat application. Aluminum and galvanized metal: A primer must be used to coat these surfaces prior to top coat application.

**APPLICATION AND CLEAN UP:** For best results apply a wet film thickness of 3.1 to 4.5 mils creating a dry film thickness of 1.1 to 1.5 mils. This product may be applied with conventional or airless spray equipment. Conventional Spray: Reduce product viscosity with water to 25 to 35 seconds in #3 Zahn cup. Airless Spray: It is recommended that the product be used as supplied in the container; however, if thinning is desired, reduce by adding 5-10% of water until desired consistency is reached. For proper curing, do not apply more than 4.5 mils thickness. Detailed application procedures for specific surfaces are available in supplier literature. Clean all brushes, rollers, or spray equipment with warm water after use.

**DRY TIME:** Heat Dry: 150°F for 5-10 minutes. Air Dry: touch, 20-25 minutes; tack-free, 30 minutes; handle, 30 minutes to one hour. Drying time may vary due to air movement and humidity.

GROCO SPECIALTY COATINGS  
10818 Hawn Freeway / Dallas, Texas 75217  
972-286-7890 FAX 972-286-8890

[www.grocosc.com](http://www.grocosc.com)



**GRO-LAC® QUICK DRY BRUSHING ENAMEL GLOSS WHITE**

**SPECIFICATIONS: 766-1205**

Solids by Weight .....	47 +/- 2.0%	
Solids by Volume .....	38 +/- 2.0%	
Theoretical Coverage (sq. ft./gal. @ 1 mil dry film) .....	609	
Viscosity (Krebs units @ 77 degrees F).....	88-92 K.U.	
Dry Time (@ 77 degrees F)	Touch .....	20-25 min.
	Re-Coat .....	3-4 hrs.
Gloss (@ 60 degrees F) .....	80-85	

**AVAILABILITY:**

Colors: White

**PRECAUTIONS:** PROTECT FROM FREEZING! CAUTION! Close container after each use. Do not take internally. Keep out of the reach of children.

**FOR FURTHER INFORMATION SEE MSDS SHEET.**

**PRODUCT DATA**

GROCO SPECIALTY COATINGS  
10818 Hawn Freeway / Dallas, Texas 75217  
972-286-7890 FAX 972-286-8890

[www.grocosc.com](http://www.grocosc.com)