



PRODUCT: GRO-LAC® ANTI-CORROSIVE RED OXIDE PRIMER

CODE: 777-4124

TYPE: ACRYLIC COPOLYMER EMULSION

PRODUCT DESCRIPTION: GRO-LAC® Anti-Corrosive Red Oxide Primer was specially formulated to meet requirements of early air dry and low temperature bake applications. It has excellent early water resistance and hardness. GRO-LAC® Anti-Corrosive Red Oxide Primer is richly pigmented and suspended in a selected blend of acrylic copolymer emulsions. It is a water-type system; therefore, it may be easily thinned with water to a desired dip or spray application.

USES: May be used on aluminum, cold rolled steel, galvanized metal, copper and most other metal substrates.

SURFACE PREPARATION: Surface to be coated must be cleaned and free of all wax, dirt, grease and any other foreign matter.

APPLICATION AND CLEAN UP: GRO-LAC® Anti-Corrosive Red Oxide Primer may be sprayed with conventional or airless spray equipment. This material may also be used for a dipping application after thinning to the proper consistency. Clean all equipment with clean, warm water after each use.

DRYING: May be air cured, oven dried or warm air dried. When oven dried, all film qualities are obtained at a much faster rate. Suggested oven dry time at 1 mil is 2 minutes at 165 degrees F.

PRODUCT DATA

GROCO SPECIALTY COATINGS
10818 Hawn Freeway / Dallas, Texas 75217
972-286-7890 FAX 972-286-8890

www.grocosc.com



GRO-LAC® ANTI-CORROSIVE RED OXIDE PRIMER

SPECIFICATIONS: 777-4124

Solids by Weight	52.86 +/- 2.0%	
Solids by Volume	39.91 +/- 2.0%	
Theoretical Coverage (sq. ft./gal. @ 1 mil dry film)	640	
Viscosity (Krebs units @ 77 degrees F).....	75-80 K.U.	
Dry Time (@ 77 degrees F)	Touch	20-25 min.
	Re-Coat	1 hr.
Gloss (@ 60 degrees F)	Flat	

AVAILABILITY:

Colors: Red Oxide

PRECAUTIONS: PROTECT FROM FREEZING! CAUTION! Close container after each use. Do not take internally. Keep out of the reach of children.

FOR FURTHER INFORMATION SEE MSDS SHEET.

PRODUCT DATA

GROCO SPECIALTY COATINGS
10818 Hawn Freeway / Dallas, Texas 75217
972-286-7890 FAX 972-286-8890

www.grocosc.com