



**PRODUCT:** PRO HYDE INTERIOR LATEX SEMI-GLOSS ENAMEL

**CODE:** 108-1005

**TYPE:** VINYL ACRYLIC EMULSION

**PRODUCT DESCRIPTION:** Pro Hyde Interior Latex Semi-Gloss Enamel is a new development of latex enamel that exhibits many advantages and improvements over other latex enamels. It may be applied over new or previously painted interior surfaces. Pro Hyde Interior Latex Semi-Gloss Enamel is a non-yellowing, easy to apply material that has excellent gloss and leveling properties and dries in a matter of minutes to a beautiful semigloss sheen. Pro Hyde Interior Latex Semi-Gloss Enamel may be scrubbed if necessary within 58 hours after paint is dry.

**SURFACE PREPARATION:** Surface to be coated must be clean and free from wax, oil and grease. Glossy surfaces should be dulled with fine grit sandpaper or a surface deglosser. Remove sanding dust from surface with a moist cloth before applying enamel. Do not apply enamel over shellac or varnish stain.

**APPLICATION AND CLEAN UP:** Stir Pro Hyde Interior Latex Semi-Gloss Enamel thoroughly before using. Do not shake. For best results, Pro Hyde Interior Latex Semi-Gloss Enamel should be applied as supplied in container; however, on extremely porous surfaces or in hot weather it may be thinned with no more than one-fourth pint of clean water to one gallon of enamel. Apply with nylon brush, short nap roller or spray equipment. Clean tools immediately after use with soapy water then rinse well with clean water. Allow four to five hours between coats. New wood or unprimed metal: Prime with Groco's Quick Wall Primer, then finish with one or two coats of Pro Hyde Interior Latex Semi-Gloss Enamel.

**SPECIAL NOTE:** This is a latex paint. Do not apply in temperatures below 45 degrees F. Do not tint with colors in oil. Do not mix with turpentine, solvent, thinners or any other paint.

PRODUCT DATA

GROCO SPECIALTY COATINGS  
10818 Hawn Freeway / Dallas, Texas 75217  
972-286-7890 FAX 972-286-8890

[www.grocosc.com](http://www.grocosc.com)



**PRO HYDE INTERIOR LATEX SEMI-GLOSS ENAMEL**

**SPECIFICATIONS: 108-1005**

Solids by Weight .....	46.54 +/- 2.0%	
Solids by Volume .....	34.59 +/- 2.0%	
Theoretical Coverage (sq. ft./gal. @ 1 mil dry film) .....	554	
Viscosity (Krebs units @ 77 degrees F).....	78-80 K.U.	
Dry Time (@ 77 degrees F)	Touch .....	1-1.5 hrs.
	Re-Coat .....	4-5 hrs.
Gloss (@ 60 degrees F) .....	50-55	

**AVAILABILITY:**

Colors: White  
Special Tints

**PRECAUTIONS:** PROTECT FROM FREEZING! CAUTION! Avoid prolonged contact with skin, eyes and breathing of vapor or spray mist. Close container after each use. Do not take internally. Keep out of the reach of children.

**FOR FURTHER INFORMATION SEE MSDS SHEET.**

**PRODUCT DATA**

GROCO SPECIALTY COATINGS  
10818 Hawn Freeway / Dallas, Texas 75217  
972-286-7890 FAX 972-286-8890

[www.grocosc.com](http://www.grocosc.com)