



TRANSSEAL® HWAS SS GEL REMOVER

Product Number 989-9106

For removal of TRANSSEAL® HWAS Coating and GRO-LAC® Amine Inks:

The removal of the HWAS series is dependent upon conditions, type of removal process and mil thickness of the coating. For **production removal** use TRANSSEAL® SS Gel Remover with a commercial pressure washer system. Apply SS Remover to the surface liberally and allow to stand approximately ten minutes or until the surface is totally wet, then high pressure wash the entire surface. For **in-house cleaning** wet area with remover wiping off any residue to achieve a clean substrate. The HWAS SS Gel Remover may also be used to remove grease, oil grime and dirt from surfaces to be painted. Always wipe surface clean before applying final paint finish. There are no silicone additives in these cleaners that might create problems when painting.

Technical Information:

Weight per gallon	8.09 lbs. +/- 2 %
pH	10 to 11.5 +/- .05 %
Theoretical Coverage	50 to 75 sq. ft. per gallon
VOC	5.56 lbs./gal.
Thinning	No
Clean up Surface Areas	High Pressure Water
Spray equipment	Airless

PRODUCT DATA

GROCO SPECIALTY COATINGS
10818 Hawn Freeway / Dallas, Texas 75217
972-286-7890 FAX 972-286-8890

www.grocosc.com